

## SOLAR REFLECTIVE INDEX OF VULKEM 951NF TOPCOAT

The topcoats of our Deck Coating Systems, including Vulkem 951NF, have been tested internally in different colors to determine the coatings' Solar Reflective Index (SRI) Value. The results are as follows:

VULKEM TOP COAT COLOR	REFLECTANCE	EMMISSIVITY	SOLAR REFLECTIVE INDEX (SRI) VALUE
Vulkem 951 NF Black	.047	0.91mV	0
Vulkem 951 NF Slate Gray	.20	0.91mV	19
Vulkem 951 NF Maple	.18	0.91mV	17
Vulkem 951 NF Gray	.34	0.90mV	37
Vulkem 951 NF Beige	.35	0.89mV	38
Vulkem 951 NF Limestone	.42	0.90mV	48
Vulkem 951 NF White	.82	0.90mV	103

Additionally, several of these coatings will aid in obtaining LEED™ credits, particularly Sustainable Sites Credits which address the heat island effect of non-roof and roof areas.

Please contact Tremco Technical Service at 866-209-2404 with any questions regarding this bulletin.